

## Belichtung nach EN ISO 105-B02: 1999

### Belichtungsverfahren 2

Firma: KVADRAT  
Artikel-Nr.: siehe unten

Material: Gewebe aus TREVIRA CS  
Artikel: Möbelstoffe - MEMORY

**Prüfbedingungen:**

Gerät: Alpha LM  
Filterkombination: 7 x IR

**Prüfparameter (Ist-Werte):**

Schwarzstandard: 42-44 °C  
Probenraumtemperatur: 34-35 °C  
relative Feuchte: 39-40 %  
Bestrahlungsstärke: 42 W/m<sup>2</sup>

Artikel	Lichteinheit – Note (Bewertung nach Lichteinheitsmaßstab)
Nr. 116	8
Nr. 136	8
Nr. 156	4 IMPROVED
Nr. 176	5
Nr. 196	4 IMPROVED
Nr. 216	8
Nr. 236	8
Nr. 256	6
Nr. 436	8
Nr. 456	6

## Belichtung nach EN ISO 105-B02: 1999

### Belichtungsverfahren 2

Firma:     KVADRAT      
 Artikel-Nr.:     siehe unten    

Material:     Gewebe aus TREVIRA CS      
 Artikel:     Möbelstoffe MEMORY    

**Prüfbedingungen:**

Gerät:     Alpha LM      
 Filterkombination:     7 x IR    

**Prüfparameter (Ist-Werte):**

Schwarzstandard:     42-44 °C      
 Probenraumtemperatur:     34-35 °C      
 relative Feuchte:     39-40 %      
 Bestrahlungsstärke:     42 W/m²    

Artikel	Lichteinheit – Note (Bewertung nach Lichteinheitsmaßstab)
Nr. 476	5 - 6
Nr. 636	8
Nr. 656	6
Nr. 676	6
Nr. 696	4 - 5 <i>IMPROVED</i>
Nr. 756	6
Nr. 776	5
Nr. 936	8
Nr. 976	5 - 6



**DANISH  
TECHNOLOGICAL  
INSTITUTE**

**Test Report no. A 560807-1**

Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

Kvadrat Holding A/S, Lundbergsvej 10, 8400 Ebeltoft	
Test material: Upholstery fabric	
Design: Memory	Received: 21-06-2013 Completed: 18-07-2013
Fibre content: 100% Trevira CS (Manufacturer's information)	Sample no.: 560807-1
Care label: (Not given)	Your ref.: Lone Henriksen

Test Methods	Results
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	696 Colour fastness: 5
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	196 Colour fastness: 5-6
<b>Colour fastness to artificial light</b> ISO 105:B02:2000/Amd.2:2000 Method 2 1-8 scale, 8 best rating Normal conditions Apparatus: Atlas Ci4000 Xenon Weather-Ometer	156 Colour fastness: 5-6

The test has been performed according to the attached conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

This report was generated by software version 2.44 of 2013-01-14.

18 July 2013, Danish Technological Institute, Textile

*Charlotte Fischer*

Charlotte Fischer  
Ph. Direct: +45 72 20 21 35  
E-mail: charlotte.fischer@teknologisk.dk

Test responsible

*Lea Larsen*

Lea Larsen  
Ph. Direct: +45 72 20 21 36  
E-mail: lea.larsen@teknologisk.dk

Co-reader