

Kvadrat A/S
Att.: Lone Henriksen
Lundbergsvej 10
DK-8400 Ebeltoft

Project no. A 1217488-25-1/103549
Page 1 of 2
Date 7 September 2004
Initials ntj/chf/ac

Gregersensvej
P.O. Box 141
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19

info@teknologisk.dk
www.teknologisk.dk


Test Report

- Material:** Sample of upholstery fabric collection in 18 colourways designated Coda.
Fibre content: 90% wool / 10% polyamide (customer's information)
- Sampling:** The test material was sent by the client and received at the Danish Technological Institute 12 July 2004.
- Method:** Colour fastness to artificial light, ISO 105-B02:1994, method 2.
Incl. AMD 1:1998 and AMD 2:2000
Normal conditions (1-8 scale, 8 best rating)
Test apparatus: Xenotest 450
- Period:** The testing was completed 6 September 2004.
- Results:** Results are given on page 2 of this report.

Terms: The test has been performed according to the rear side conditions, which are according to the guidelines laid down by DANAK (The Danish Accreditation). The testing is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

7 September 2004, Danish Technological Institute, Textile


Naja Johansen
Signatory


Charlotte Fischer
Counter-signatory

Results:	<u>Designation – Coda</u>	<u>Colour fastness to artificial light</u>
	100	≥ 6-7
	130	6-7
	160	6
	191	6
	910	6
	107	≥ 6-7
	710	6
	197	6
	137	6-7
	700	5-6
	196	6
	660	6
	116	≥ 6-7
	610	6
	166	6
	103	6-7
	194	6
	410	6

Remark: The exposed test specimens are enclosed.