



Report 62260 Test Report

Applicant

Kvadrat A/S
Lundbergsvej 10
8400 Ebeltoft
DÄNEMARK

Reference

Lone Henriksen

Application

Determination of burning behaviour and smoke emission.

Test Material

"Molly"

Material used in testing was anonymized for laboratory purposes. A detailed sample list is contained in the report.

Issuing and Signatures

Number of pages contained: 4

Original Issue / Vienna 2009-11-30 / mp/KK21001832

Authorised for Institute
DI (FH) Angelika Hönecke

.....
Flaw: 9

Technology Build and Live
Ing. Hannes Vittek ☎ 18 / vittek@oeti.at





Contents

1	Order	2
1.1	Chronology	2
1.2	Samples.....	2
2	Findings / Tests performed.....	2
2.1	Description of the specimen	2
2.2	Determination of burning behaviour of upholstery fabrics	3
2.3	Determination of smoke emission.....	4
3	Remarks	4

1 Order

1.1 Chronology

<i>Date</i>	<i>Received</i>	<i>Order</i>
2009-11-10	2009-11-12	Determination of burning behaviour and smoke emission.

1.2 Samples

<i>No.</i>	<i>Received</i>	<i>Sample Identification</i>	<i>Sample Material</i>
1	2009-11-12 ⁽¹⁾	"Molly"	textile fabric, approx. 2 m

(1) Samples provided by the customer. (2) Sample drawn by ÖTI.

2 Findings / Tests performed

2.1 Description of the specimen

Description of the specimen according to DIN 60 000

Test results

Tested sample: 1

Type of fibre according to DIN 60 001 part 1	100 % Wool (declaration by the applicant)
Technological description	woven fabric

2.2 Determination of burning behaviour of upholstery fabrics

Test conditions

According to ÖNORM B 3825

Arrangement of upholstery: Arrangement A - free chosen Upholstery

Kind of upholstery: foam: polyurethan foam , properties: Burning behavior:

B2 according ÖNORM B 3800-1, Designation: K 5560, Producer: Eurofoam

Number of test specimens: Longitudinal direction 3 / Cross direction 3

Test results

Tested sample: 1

Specimen	Burning-time [s]	After-flame-time [s]	After-glow-time [s]	Flame spread rate [mm/s]	self-extinguishing before reaching the mark
Longitudinal direction					
1	none	0	0	0	yes
2	none	0	0	0	yes
3	none	0	0	0	yes
Cross direction					
1	none	0	0	0	yes
2	none	0	0	0	yes
3	none	0	0	0	yes

Secondary effects of burning: melting of the specimen within the inflammation-area
self-extinguished of the covering fabric
self-extinguished of the upholstery

Opinion

According to ÖNORM B 3825 the tested specimen can be classified as
"schwerbrennbar gemäß ÖNORM B 3825"

Comments:

This test is a compound test at which the furniture fabric will always be tested combined with upholstery. Classification, therefore, relates only to the described arrangement of specimens and foam used.

We would like to point out, that according to building and fire police by-laws it is not allowed to use upholstery of burning class B 3 - highly burnable - according to ÖNORM B 3800, Part 1 (see comments on ÖNORM B 3825), for rooms of milling crowds, like theatre and meeting rooms, hotels and the catering industry.

2.3 Determination of smoke emission

Test Conditions

Standard: ÖNORM A 3800 part 1/4.2
Specimen: textile fabric
Changes to standard: none

Test results

Tested sample: 1

smoke emission [%]					
Test 1	Test 2	Test 3	Test 4	Test 5	Mean Value
1	3	5	0	0	2

Classification

The tested specimen can be classified according to ÖNORM A 3800-1, item 4.2.1 as:

Qualmbildungsklasse Q1 - schwachqualmend

Period of validity

According to ÖNORM A 3800 part 1 present test report remains valid until **November 2013**.

3 Remarks

Sample Material

Results of performed tests only refer to the sample material provided.

Without explicit written other agreement testing is destructive and the sample material is transferred to the property of ÖTI, which is entitled to freely decide on storage and disposal.

Quality management and accreditations

All tests and services are performed under a quality management system according to EN ISO 17025.

ÖTI is accredited by several organisations for various tests offered. It also is a Notified Body for several directives with the registration number 0534 (see <http://ec.europa.eu/enterprise/newapproach/nando/>). The accreditation by the Federal Ministry of Economy, Family and Youth as testing laboratory was repeated under reference 92.714/0560-1/12/2009 (Individual accredited test procedures are marked with the federal laboratory logo), the accreditation for testing and inspection of construction products was given by the OIB (Austrian Institute of Construction Engineering). Details and other accreditations are given on request and can be found on www.oefi.at.

Issuance

The valid first issue is done in paper and has single-handed signatures. For reference purposes and filing an unsigned electronic duplicate can be delivered in pdf format. Duplicates and translations will be marked accordingly on the cover sheet.

Copyright und Usage Notes

It is pointed out, that any alterations, amendments or falsifications of reports not authorized by the issuer of the report will be prosecuted as civil and criminal offences; this especially to the appropriate requirements of ABGB, UrhG, UWG and criminal law and their respective international equivalents.

Reports are protected under international copyright laws. Written consent of the ÖTI is required for publications (also in excerpt) and reference to tests for public relation purposes. Reports may only be reproduced in full length.