

**Test report Martindale Abrasion
NS-EN 12947-2 :1999**

Client SAHCO Hesslein GmbH & Co. KG KREUZBURGER STRASSE 17-19 9047 1 NÜRNBERG Tyskland		Product Fanello (2423) Product specification - tested object	
Client's reference Sarah Kemmerer		R-no. R15433	
Date 20.04.2015	Date of receipt, tested object 08.04.2015	Test completed date 17.04.2015	Rev. no. / Rev. date 0/

Manufacturer:

Composition: 81% CV/17% LI/2% PA

Pressure : 795 g(12 kPa) Type felt: Woven

The samples are conditioned at 20 degrees C and 65 % relative humidity for 18 hours

Determination of the abrasion resistance of textiles on a Martindale testmachine according to NS-EN 12947-2. Circular specimens of fabric are abraded against a reference fabric.

For woven fabrics the resistance to abrasion is estimated by number when two threads are broken.

For pile fabrics the resistance to abrasion is estimated by the number of cycles when the pile is fully worn off. For nonwovens the resistance to abrasion is estimated by the number when there is a hole of 0.5mm.


The average of four samples gives the results.

Sample no. 1: >100000
Sample no. 2: >100000
Sample no. 3: >100000
Sample no. 4: >100000
Average 4 Samples: >100000

Comments: Test stopped at 100000

REF.NR:

R15433



Test stopped at 100000