



Waterborn

Abrasion

Approximately 100.000 rubs according to the Martindale method EN ISO 12947

Pilling

Note 4-5, EN ISO 12945

Lightfastness

Note 4-7, ISO 105-B02

Flame resistance

EN 1021-1

US Cal. Tech. Bull. 117, Sec. E

With flameretardant treatment:

EN 1021-1/2

BS 5852, ignition source 5

DIN 4102 B1

SN 198 898 5.3

ÖNORM B1 Q1

UNI 9175 11M

FMVSS 302

IMO A.652(16)

Quality benefits

Good abrasion

Low pilling

Can be washed if loose covers

Environmental benefits

Innovative production with a lower environmental impact than conventionally produced microfiber fabrics

Generates 35% less CO₂

No solvents used

Recycling of water. Uses 70% less water than conventional methods

No use of AZO dyes, which may split off carcinogenic acrylamines

No use of dyes containing heavy metals

Formaldehyde < 75 ppm

No use of brominated flameretardants

Complies with REACH regulation

For further information

www.kvadrat.dk

Waterborn

Design: Aggebo & Henriksen

Composition: 85% polyester, 15% polyurethane
water repellent

Binding: non woven

Width: 140 cm

Weight: Approximately 600 g/lin.m

Cleaning:

Loose covers: Washable at maximum 60°C

Dripdrying. Shrinkage approximately 2%

Fixed covers: Dry cleaning

Stain removal: See special guide