



Textiles F.R. Limited
Flame Retardancy Finishers & Consultants

Unit 4B, (30) Wharfedale Road
Euroway Trading Estate
Bradford
West Yorkshire
BD4 6SG

Tel: 01274 651230
Fax: 01274 651305
E-mail: sales@textilesfr.co.uk
Web site: www.textilesfr.co.uk



Test Report & Certificate

UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 20776 Page 1 of 1
Test Method : BS EN ISO 15025:2002 Duplicate Document 1
Specification: BS5867-2:2008:Type B Contract Curtain Test

Customer Account: SAH003
SAHCO GMBH
KREUZBURGER ST 17-19
D-90471 NURNBERG
GERMANY

Order Details
TFR Order No : 245372
Customer Order : SK
Order Date : 09/07/2018
Fabric Description : AVALON
Fabric Composition :
Quantity (metres) : 1.0

Sample Conditioning : Test specimens were conditioned in an atmosphere having a temperature of 20°C +/- 2°C and Relative Humidity 65% +/- 5 % for a minimum of 24 hours prior to testing.
Test Enclosure Conditions : Temperature 20 °C Relative Humidity 66 %
Cleansing Procedure : Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.
Other Details :
Sample Treatment : Sample tested in an as received state

Test Procedure:
Six specimens were prepared each measuring 200mm +/- 2mm x 160mm +/- 2mm, three with the longer dimension in the length and three with the longer dimension in the width. A butane flame was applied to the sample face for 15 seconds.



Report Notes:
This test was carried out in accordance with BSEN ISO 15025 Procedure A. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

OBSERVATIONS	Warp Direction			Weft Direction		
	Rep1	Rep2	Rep3	Rep1	Rep2	Rep3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No

Comments:

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867-2:2008:Type B Flammability testing was performed without the durability requirements stated in Section 5 of BS5867-2:2008 being completed.

Conducted by : Mr.R. BERRY  Date 25/07/2018
Laboratory Technician
Authorised by: Miss K. BUTTON  Date 25/07/2018